

COATING SPECIFICATION

SUBSTRATE: Exterior Hard or Soft Wood Windows, Doors, Soffits and Fasciae – New – Paint

SURFACE PREPARATION & APPLICATION:

- Proper surface preparation is crucial to maximum finish performance. The durability of this product can be impaired by an unsound or poorly prepared surface.
- The moisture content of the wood should be less than 15%.
- Apply evenly with a good quality synthetic bristle brush. DO NOT use a natural bristle brush with water based products.
- Fill with suitable filler and sand where required. Remove dust.

HARD WOOD

1st coat: Colourtrend Prime3 OIL

2nd coat: Colourtrend Prime3 OIL

3rd coat: Colourtrend Gloss or Satin in desired colour

4th coat: Colourtrend Gloss or Satin in desired colour*

NOTES:

- Oily hardwoods e.g. Iroko, Sapele, Meranti require a rub down with methylated spirits before work commences.
- Coating will achieve full adhesion after seven days
- For greater block resistance we recommend using Colourtrend Gloss

SOFT WOOD

Treat any knots with 2 coats of Colourtrend Prime1 ACRYLIC - UNTHINNED†

1st coat: Colourtrend Undercoat

3rd coat: Colourtrend Gloss or Satin in desired colour

4th coat: Colourtrend Gloss or Satin in desired colour*

*Some colours may require extra coats

†Do not thin Colourtrend Prime1 ACRYLIC as this will hinder its stain locking properties

NOTES:

- For knot treatment: allow at least 4 hours before applying the second coat of Prime1 ACRYLIC
- Coating will achieve full adhesion after seven days
- For greater block resistance we recommend using Colourtrend Gloss



INFINITE COLOUR *from* IRELAND

Colourtrend, Maynooth Road, Celbridge, Co Kildare, W23 X7R8, Ireland

t: +353 1 6288224 **f:** +353 1 6272205 **e:** info@colourtrend.ie

IMPORTANT NOTE: The information contained in this specification sheet is not intended to be conclusive. It is for guidance and is given in good faith. Whilst we attempt to ensure that all advice we give about our products, whether in this sheet or otherwise, is correct, we have no control over the quality or condition of the substrate or the many factors affecting the use and application of this product. Many such factors are beyond our control and it is always good practice to conduct a trial area in advance to ensure a satisfactory result.