

COATING SPECIFICATION

SUBSTRATE: Exterior Masonry – New sand/cement render – Paint

SURFACE PREPARATION:

- Allow fresh plaster to dry out fully. When dry, it will be uniform in colour. This may, depending on weather conditions, take up to six weeks after plastering.
 - Older unpainted plaster may require pre-treatment with Colourtrend Weather Fungicidal Wash if fungal growths are present. Apply as per instructions on container.
 - Brush down surface with stiff brush to remove any cement residues (laitance). Skip this step if power washing is going to take place.
 - Older unpainted plaster may require power washing at circa 1500psi if dirt or grime is present.
 - If power washing leave surface to dry before applying first coat.
 - Make good any large cracks with suitable acrylic caulk and smaller cracks with masonry filler.
- Dab with a damp sponge to feather edges of filler.
- Chalky or flaky masonry requires Colourtrend Weather Stabilising Primer as the first coat.
 - Dense masonry and mass concrete, e.g. window sills and cappings, require Colourtrend Weather Stabilising Primer as the first coat.

COATING:

1st coat: Colourtrend Weather Exterior Masonry Paint in desired colour diluted with 5-10% water.

2nd coat: Colourtrend Weather Exterior Masonry Paint in desired colour

3rd coat: Colourtrend Weather Exterior Masonry Paint in desired colour

APPLICATION:

- Brush, roll or spray
- Ensure good drying conditions during application and drying.
- Do not apply if surface or ambient temperature is below 10°C.
- Do not apply if there is a risk of surface moisture or surface temperature falling below 10°C within 6 hours of finishing painting.
- Do not apply in direct sunshine or if surface temperature is warm to touch.

NOTES:

- For a soft sheen finish the final coat can be replaced with Colourtrend Soft Sheen.



INFINITE COLOUR *from* IRELAND

Colourtrend, Maynooth Road, Celbridge, Co Kildare, W23 X7R8, Ireland

t: +353 1 6288224 **f:** +353 1 6272205 **e:** info@colourtrend.ie

IMPORTANT NOTE: The information contained in this specification sheet is not intended to be conclusive. It is for guidance and is given in good faith. Whilst we attempt to ensure that all advice we give about our products, whether in this sheet or otherwise, is correct, we have no control over the quality or condition of the substrate or the many factors affecting the use and application of this product. Many such factors are beyond our control and it is always good practice to conduct a trial area in advance to ensure a satisfactory result.